

## WinFlow™ PR 30WME

Water reducing, retarding plasticizer for concrete.

---

### Product description

WinFlow PR 30WME is a chloride free plasticizing retarder based on sugar reduced lignosulphonate, and workability retention agents.

---

### Application

- Ready mixed and site batched concrete.
  - Micro silica and GGBS modified concrete where durable and low permeability concrete is required.
  - Long haul and hot weather concreting
- 

### Features/benefits

- Concrete with better workability, allowing easier concrete placement
  - Concrete with lower water cement ratio minimizes the risk of segregation and bleeding and assist in production of dense higher early and ultimate strength low permeability concrete .
  - Suitable for reinforced pre stressed concrete.
- 

### Tests /standards

Complies with ASTM C-494 type –D and G & EN 934-1:2008

---

### Typical properties

Appearance	:	Dark brown liquid
Specific gravity @ 25 <sup>0</sup>	:	1.13± 0.03
pH	:	5.42±1
Chloride content	:	Chloride free

---

### Technical support

WME provides a comprehensive technical support services to specifiers, end users and contractors, and is able to offer onsite technical assistance.

---

### Recommended dosages

0.4 to 1.4 liters/100 kg of cementitious material. Dosage will vary according to concrete property requirement and mix design. Dosage other than recommended dosages is not uncommon. Lab and site trials are necessary to ascertain the optimum dosages for particular application.

---

### Compatibility

WinFlow PR 30WME is compatible with other WME admixtures. All admixtures should be added to the concrete mix separately and must not be mixed together prior to addition. The resultant properties of the concrete containing more than one admixture should be assessed by trial mixes. WinFlow PR 30WME is suitable for use with all types of portland cement and cement replacement materials such as PFA, GGBS and micro silica.



Window Into Construction

## Effects of over dosages

Over dosages, may result in increase in workability, set retardation and increase in air content. The ultimate strength of the concrete will not be impaired by increased retardation, provided that adequate curing is maintained.

---

## Curing

Fresh concrete must be cured properly, especially at high temperatures in order to prevent plastic and drying shrinkage, using WME curing compounds.

---

## Packaging

**WinFlow PR 30WME** is available in 200 Litre drum or bulk supply.

---

## Storage and shelf life

**WinFlow PR 30WME** can be kept 12 months from date of manufacture if stored in well protected area away from sunlight, at ambient temperature in dry conditions.

---

## Health and safety information

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent material safety data sheet containing physical, ecological, toxicological and other safety-related date.

---

## Legal note

The information, and, in particular, the recommendations relating to the application and end-use of WME products, are given in good faith based on WME 's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with WME's recommendations. In practice, the differences in materials, substrates and actual site condition are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Users must always refer to the most recent issue of the product data sheet for the product concerned, copies of which will be supplied on request.

Rev: March, 2015

In Association with Kirton Concrete Services UK

**UK Office**  
WinChem Construction Chemicals LTD.  
Sydney Road, Watford,  
WD 187QX  
United Kingdom  
Email: ukcorp@winchemme.com



**Factory**  
WinChem Industries L.L.C.  
P.O. Box: 3430, Umm Al Quwain, U.A.E.  
Tel: +971 6 7667581  
Fax: +971 6 7667582  
Email : info@winchemind.com