

WinFlow™ SP 607WME

High range water reducing concrete admixture

Product description

WinFlow SP 607WME is specifically meant for concrete with low water cement ratio, high slump retention and high strength concrete.

Application

- To provide initial workability especially with lower water /cement ratio
 - To significantly improve the initial workability of site mixed concrete without increasing water demand.
 - To provide improved durability by increasing ultimate strength and reducing concrete permeability
-

Features /benefits

- Powerful plasticizing action with an improved initial workability
 - Improved cohesion and particle dispersion minimizes segregation and bleeding and improves pump ability.
 - Long haul and hot weather concreting
 - Gains early strength with very high slump retention
-

Tests/ standards

Complies with ASTM C-494 type –F and G & EN 934 -1 :2008

Typical properties

Appearance	: Dark brown liquid
Specific gravity @ 25 ⁰ C	: 1.23±0.03
pH	: 6.03±1
Chloride content	: Chloride free

Technical support

WME provides a comprehensive technical support services to specifies, end users and contractors and is able to offer onsite technical assistance.

Recommended dosages

0.4 to 2.3 liter/100 kg of cementitious materials. Dosage will vary according to concrete property requirement and mix design. Dosage other than recommended dosages is not uncommon. Lab and site trials are necessary to ascertain the optimum dosages for particular application.

Compatibility

WinFlow SP 607WME is compatible with other WME admixtures. All admixtures should be added to the concrete mix separately and must not be mixed together prior to addition. The resultant properties of the concrete containing more than one admixture should be assessed by trial mixes. WinFlow SP 607WME is suitable for use with all types of portland cement and cement replacement materials such as PFA, GGBS and micro silica.



Window Into Construction

Effect of over dosages

Over dosages, may result in increase in workability, set retardation and increase in air content. The ultimate strength of the concrete will not be impaired by increased retardation, provided that adequate curing is maintained.

Curing

Fresh concrete must be cured properly, especially at high temperatures in order to prevent plastic and drying shrinkage, using WME curing compound.

Packaging

WinFlow SP 607WME is available in 200 Litre drum or bulk supply.

Storage and shelf life

WinFlow SP 607WME can be kept 12 months from date of manufacture if stored in well protected area away from sunlight, at ambient temperature in dry conditions.

Health and safety information

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent material safety data sheet containing physical, ecological, toxicological and other safety-related data.

Legal note

The information, and, in particular, the recommendations relating to the application and end-use of WME products, are given in good faith based on WME 's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with WME's recommendations. In practice, the differences in materials, substrates and actual site condition are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Users must always refer to the most recent issue of the product data sheet for the product concerned, copies of which will be supplied on request.

Rev: March, 2015

In Association with Kirton Concrete Services UK

UK Office
WinChem Construction Chemicals LTD.
Sydney Road, Watford,
WD 187QX
United Kingdom
Email: ukcorp@winchemme.com



Factory
WinChem Industries L.L.C.
P.O. Box: 3430, Umm Al Quwain, U.A.E.
Tel: +971 6 7667581
Fax: +971 6 7667582
Email : info@winchemind.com